ArcheoSciences

Revue d'archéométrie

33 | 2009

Authentication and analysis of goldwork

Modern mineralogy of gold: overview and new data

Minéralogie moderne de l'or : bilan et nouvelles données

Ernst Spiridonov and Denka Yanakieva

Electronic version

URL: <http://journals.openedition.org/archeosciences/2034>

DOI: 10.4000/archeosciences.2034

ISBN: 978-2-7535-1598-7

ISSN: 2104-3728

Publisher

Presses universitaires de Rennes

Printed version

Date of publication: 31 December 2009

Number of pages: 67-73

ISBN: 978-2-7535-1181-1

ISSN: 1960-1360

Electronic reference

Ernst Spiridonov and Denka Yanakieva, « Modern mineralogy of gold: overview and new data », *ArcheoSciences* [Online], 33 | 2009, Online since 09 December 2012, connection on 19 April 2019. URL : <http://journals.openedition.org/archeosciences/2034> ; DOI : 10.4000/archeosciences.2034

Modern mineralogy of gold: overview and new data

Minéralogie moderne de l'or : bilan et nouvelles données

Ernst SPIRIDONOV* and Denka YANAKIEVA**

Abstract: We suppose that it should be useful for archaeologists to have an overview on gold mineralogy, because 1) in ancient times, part of the golden objects were made directly from natural golden nuggets; 2) most of the Au in ores exists as its own minerals. The major part of the Au in the planets and meteorites of our Solar system is found in high temperature solid solutions: metallic Fe-Ni and monosulfides Fe-Ni and Fe-Cu. Au leaves them under fluid or some other reworking. As a result, Au minerals are formed. They are mainly developed in hydrothermal deposits of the upper part of Earth's continental crust. Au is the noblest chemical element. Thus, the most part of Au in deposits appears as native gold: Au-Ag, Au-Ag-Hg, Au-Cu, Au-Pd, and Au-Pt system minerals. The most important feature of native gold is its fineness, i.e. the Au content in the mineral species, expressed in ‰. Chalcogenides of Au – sulfides and selenides, and, similar to them, tellurides, plumbotellurides, antimonides, bismuthides – are not so widespread. Data on the 44 Au mineral species known today are provided in this overview. The first quantitative estimations of natural native gold nano-dimensional crystallites of several mesothermal deposits are enclosed.

Résumé : Nous supposons qu'il est important pour les archéologues d'avoir une vue générale sur la minéralogie de l'or car : 1) dans le passé une partie des objets en or ont été produits directement à partir de pépites d'or ; 2) la plus grande partie de l'or existe sous la forme de ses propres minerais. La plus grande partie de l'or dans les planètes et les météorites de notre système solaire se trouve en solutions solides à haute température : Fe-Ni métallique et Fe-Ni monosulfites et Fe-Cu. L'or les laisse sous la forme de fluides ou sous une forme équivalente. Le résultat est la formation de minerais d'or. Ces minerais sont essentiellement développés dans des gisements hydrothermaux de la partie supérieure de la croûte terrestre. L'or est l'élément chimique le plus noble. Pour cette raison, la majorité de l'or dans les gisements se présente sous forme native : systèmes minéraux Au-Ag, Au-Ag-Hg, Au-Cu, Au-Pd, Au-Pt. La caractéristique la plus importante de l'or est son titre, c'est-à-dire la quantité d'or dans les espèces minérales en ‰. Chalcogénides d'or – sulfites et sélénites et similaires comme les tellurites, plumbotellurites, antimonides, bismuthides – sont moins répandus. Les données des espèces minérales ⁴⁴Au connues actuellement sont fournies dans cet article. Les premières estimations quantitatives de cristallites nano-dimensionnelles d'or natif naturel de divers gisements mesothermiques ont aussi été incluses.

Keywords: mineralogy, gold, nanomineralogy.

Mots-clés : minéralogie, or, nano-minéralogie

1. INTRODUCTION

The major part of the Au in the planets and meteorites of our Solar system is found in high temperature solid solutions – metallic Fe-Ni and monosulfides Fe-Ni (Mss) and Fe-Cu (Iss). Au leaves them under fluid reworking. As a result, Au minerals are formed. They are mainly developed in hydrothermal

deposits of the upper part of Earth's continental Earth. Au is the noblest chemical element. Thus, the most part of Au in deposits appears as native gold – Au-Ag, Au-Ag-Hg, Au-Cu, Au-Pd, and Au-Pt system minerals. The most important feature of native gold feature is its fineness, i.e. the Au content in the mineral specimen, expressed in ‰. Chalcogenides of Au – sulfides and selenides, and, similar to them, tellurides, plumbotellurides,

---

* Department of Mineralogy, Lomonosov State University of Moscow – Vorobiovy Gory, 1192334, Russia. (mineral@geol.msu.ru)

** Museum "Earth and Man" – Boulevard Cherny Vrch 4, Sofia, 1421, Bulgaria. (denkay@abv.bg)

antimonides, bismuthides – are not so widespread. Much Au is found as the finest impurity in hydrothermal nonstoichiometric As-bearing pyrite $\text{Fe}(\text{S}_{\text{As}})_{2-x}$ and arsenopyrite $\text{FeAs}_{1-y}\text{S}_{1+y}$ and bitumen-like Au-organic compounds.

2. AU – AG SYSTEM MINERALS

The main part of native gold appears as cubic solid solutions – Au-Ag system minerals. According to the results of thousands of precision analyses (Brauns, 1906; Vernadsky, 1914; Lindgreen, 1933; Smolin, 1970; Editorial Committee, 1970; Petrovskaya, 1973; Berman *et al.*, 1978; Nedra, 1984-1990; Oberthür and Saager, 1986; Shikazono and Shimizu, 1987; Amuzinsky *et al.*, 1992; Nekrasov *et al.*, 1994; Spiridonov, 1995; So *et al.*, 1995; Frimmel and Gartz, 1997; Hytönen, 1999; Knight and Leitch, 2001, etc.) it was established that the series Au-Ag is uninterrupted in composition. These series are fixed in the limits of the series (Vernadsky, 1914; Petrovskaya, 1973): **gold** (0-30 wt% Ag; fineness 1000-700); **electrum** (30-70 wt% Ag; fineness 700-300); **kuestelite** (70-90 wt% Ag; fineness 300-100); gold-containing **silver** (90-100 wt% Ag; fineness 100-0). The confirmed mineral species are noted in bold. On observations of the authors, the phenomena of disintegration of solid solution in Au-Ag minerals are not shown. The size of gold crystals varies from colloidal (< 0.1 microns) up to several cm, usually around a fraction of mm. Colloidal gold colours a chalcedony-like quartz in green colour (Baley, Transbaykalia). The size of the granulated intergrowths of gold (nuggets) is up to one metre. As Al-Biruni (1963) noted, the largest nugget of gold discovered weighed ~ 2500 kg (Zaruban, Afganistan).

High-standard gold (Fig. 1) is typical for plutogenic hydrothermal gold-quartz deposits. These formations are the main source for placer Au deposits. Electrum, kuestelite and Au-bearing silver, their dendrites, skeletal and wire-shaped crystals (Fig. 2) are typical for volcanogenic hydrothermal Au-Ag deposits (Goldschmidt, 1918; Lindgreen, 1933; Petrovskaya, 1973). Widespread in these deposits, electrum corresponds to the famous 'electron' of the ancient Greeks, and the favourite 'white gold' of the Incas.

Gold crystals of primary endogenic deposits are zonal: later zones are enriched by Ag and Hg (usually insignificantly). In metamorphosed deposits, grains of gold are azonal, and intergrowths of different composition are observed (Frimmel and Gartz, 1997). In placers, grains of gold are usually enclosed by margins of porous high-standard gold; silver from these margins is leached. In placers, native gold often is found together with minerals of platinum group elements (ferroplatinum Pt_3Fe , alloys Os-Ir-Ru, etc.).

Figure 1: (See colour plate) Gold (fineness 885) in quartz vein. 81 mm. Bestube, Northern Kazakhstan. Collection and photography – E.S. Perhaps this deposit was one of the gold sources for the well known ancient Scythian jewellery.

Figure 1 : (Voir planche couleur) Or (titre 885) dans le filon de quartz. Bestube, nord du Kazakhstan. Collection et photographie – E.S. Peut-être ce gisement a été une source d'or, exploité pour la production d'orfèvrerie Scythe.

3. AU (AG) – HG SYSTEM MINERALS

After Ag, Hg is the second most typical element impurity in native gold. In ores formed under low $f\text{S}_2$ conditions, there are cubic α -amalgams: **mercurian gold** (Au, Hg) (Nazmova and Spiridonov, 1979; Oberthür and Saager, 1986; Shikazono and Shimizu, 1988; Amuzinsky *et al.*, 1992); **mercurian electrum** (Au, Ag, Hg), **mercurian kuestelite** (Ag, Au, Hg), gold-containing **mercurian silver** (Spiridonov and Pletnev, 2002). Mercurian gold contains up to 18 wt% Hg, and mercurian silver up to 26% Hg. Au amalgams enriched by Hg are much more rare. They usually associate with native Hg: hexagonal **weishanite** (Au,Ag)₃Hg₂ (Li *et al.*, 1984; Wu, 1993); cubic **gold amalgama** $\gamma\text{-Au}_2\text{Hg}_3$ (Berman and Harcourt, 1938). Almost all Au amalgams found in placer deposits are technogenic formations (Wu, 1993).

4. AU – CU SYSTEM MINERALS

Cu is the third most typical element impurity in native gold, after Ag and Hg. Au-Cu phases poor in silver and Au-Ag phases poor in copper are formed at temperatures below 350 °C (Lyakischev, 1996). Au-Cu minerals (cuprian

Figure 2: (See colour plate) Golden wire in calcite. 4 mm. Tyrny-Auz, Northern Caucasus. Collection of V. Andreenko. Photography – M. Bogomolov.

Figure 2 : (Voir planche couleur) Fil d'or dans de la calcite. 4 mm. Tyrny-Auz, nord du Caucase. Collection de V. Andreenko. Photographie M. Bogomolov.

gold) are found in hydrothermal Au deposits, among listvenitized peridotites, komatiites and rodingites (Lozechkin, 1939; Spiridonov and Pletnev, 2002). These last minerals replace native copper. Cubic **auricupride** AuCu_3 is known (Ramdohr, 1967). Metastable **cuproauride** AuCu corresponds to the low ordered α -(Au, Cu) solid solution (Lozechkin, 1939; Chvileva *et al.*, 1988). The mineral corresponding to the Au_3Cu cubic modification (Knipe and Fleet, 1997; Spiridonov and Pletnev, 2002) does not have an authorized name. Below, it is referred to as **mineral** Au_3Cu . The products of cuproauride solid phase transformation are tetragonal **tetraauricupride** AuCu (Chen *et al.*, 1982). Tetraauricupride can contain up to 17 wt% Pd (Spiridonov *et al.*, 2003). Tetraauricupride – hongshiite CuPt solid solutions are known (Kwitko *et al.*, 2002). After annealing, non-stoichiometric cuproauride Au_{1+x}Cu shows two types

of thin lattice solid solution disintegration structures: Au + tetraauricupride and tetraauricupride + mineral Au_3Cu . The disintegration structures are known, where the matrix is Au and lamellas are mineral Au_3Cu ; probably they are products of the non-stoichiometric mineral Au_{3+x}Cu 's disintegration. The standard roentgenometric data that are required for the determination of Au-Cu system minerals are provided in Chvileva *et al.* (1988).

5. AU – FE SYSTEM MINERALS

It was established by a combination of magnetometric and mineralogical methods that the high-magnetic ferrous gold with 4-5 wt% Fe described earlier shows fine crystal intergrowths of gold with 0-0.2 wt% Fe, and magnetite octahedrons 0.01-0.2 microns in size (Yacubovskaya *et al.*, 1989).

6. AU – PD, PT, OS, IR SYSTEM MINERALS

Au-Pd and Au-Pt system minerals are typical rare minerals of telethermal Au deposits formed at low $f\text{S}_2$ and at heightened $f\text{O}_2$. They are cubic **palladian gold (porpezite)** (Au, Pd). (Vernadsky 1914; Kwitko *et al.*, 2002); **platinian gold (Au, Pt)** (Levin *et al.*, 1986); intermetallides with compositions similar to Pt_3Au and $\text{Pt}(\text{Au}, \text{Pd})$. Even a low impurity of Pd (of the order of a few percent) results in the steel-grey colour of this type of native gold.

7. AU – BI, SB, PB, SN SYSTEM MINERALS

Intermetallides of gold – **maldonite** Au_2Bi (Hytönen, 1999) and **aurostibite** AuSb_2 (Graham and Caiman, 1952; Spiridonov, 1995) are rather rare minerals of hydrothermal ores. Maldonite contains ~ 65 wt% Au, and aurostibite ~ 45 wt% Au. Aurostibite pseudomorphs after maldonite are rarely encountered; such aurostibite contains up to 9 wt% Bi. These minerals are formed under low $f\text{S}_2$. Maldonite usually replaces native bismuth. Aurostibite usually replaces native gold. The following three intermetallides: **anyuiite** AuPb_2 (Razin and Sidorenko, 1989), **hunchunite** Au_2Pb (Shangquan *et al.*, 1992), **yuanjiangite** AuSn (Chen Lichang, 1994) are found only in placers. Perhaps these three intermetallides are technogenic products.

8. Au – Ag (Cu) – Te SYSTEM MINERALS

Au and Ag tellurides are typical minerals of hydrothermal Au deposits. In a series of cases, they are the main Au and Ag bearing minerals in ores. Hg and Cu are typical elemental impurities in these tellurides. Triclinic **montbrayite** $\text{Au}_2(\text{Te}_{\text{Sb,Pb,Bi}})_3$ (Peacock and Thompson, 1946; Chvileva *et al.*, 1988) is a rare telluride, and it contains ~ 50 wt% Au and up to 5 wt% Sb. Monoclinic **calaverite** AuTe_2 (Stillwell, 1931; Markham, 1960) contains ~ 45 wt% Au, and usually < 0.5 wt% Ag. In some deposits (Kalgoorly, Australia), there are calaverite aggregates reaching 1 m^3 in size. Rhombic **krennerite** $\text{Au}_3(\text{Au,Ag,Cu})\text{Te}_8$ (Markham, 1960; Editorial Committee, 1970; Chvileva *et al.*, 1988) contains ~ 40 wt% Au, and 0.5–6.5 wt% Ag; its composition varies from AuTe_2 to Au_3AgTe_8 . Monoclinic **silvanite** $\text{Au}(\text{Ag,Au,Cu})\text{Te}_4$ (Stillwell, 1931; Markham, 1960; Editorial Committee 1970; Chvileva *et al.*, 1988) contains ~ 25 wt% Au. **Kostovite** $\text{Au}(\text{Cu,Ag,Au})\text{Te}_4$ (Terziev, 1966), similar to silvanite, is a typical reactionary mineral of volcanogenic Au ores. **Mutmannite** AuAgTe_2 (Spiridonov and Chvileva, 1985), developed in the cementation zone of the gold-telluride deposits, is an example of mimicry in the mineral kingdom, because it is indistinguishable from petzite optically and on spectra of reflection light, and from calaverite according to the X-ray pattern. Cubic **petzite** AuAg_3Te_2 (Markham, 1960; Chvileva *et al.*, 1988) with garnet-like structure is the most widespread Au-Ag telluride; it contains ~ 25 wt% Au. Cubic **solid solution** $(\text{Ag,Au})_2\text{Te}$ is rarely encountered as homogeneous phase; usually it is transformed into petzite and hessite intergrowths.

9. Au – Ag – Se, S SYSTEM MINERALS

Cubic **fischesserite** AuAg_3Se_2 (Johan *et al.*, 1971), cubic **uytenbogaardtite** AuAg_3S_2 (Barton *et al.*, 1978), monoclinic **petrovskaitite** $\text{AuAgS} - \text{AuAg}(\text{S,Se})$ (Nesterenko *et al.*, 1984; Nekrasov *et al.*, 1988), hexagonal **penzhinite** $\text{AuAg}_4(\text{S,Se})_4$ (Bochek *et al.*, 1984), cubic **solid solution** $(\text{Ag,Au})_2\text{Se}$ (Spiridonov *et al.*, 2009), cubic **solid solution** $(\text{Ag,Au})_2\text{S}$ (Samusikov *et al.*, 2002) are typical minerals of Au volcanogenic hydrothermal deposits, from low sulfide to rich sulfide ones. Petrovskaitite is also developed in crusts of weathering of sulfide rich deposits, in association with jarosite and native sulphur.

10. COMPLEX CHALCOGENIDES

Rhombic **nagyágite** $\text{AuPb}_5\text{Te}_{4-x}(\text{Sb,As})_x\text{S}_6$ (Spiridonov, 1991a; Simon *et al.*, 1994) – $\text{AuPb}_5\text{Te}_2(\text{Sb,Bi})\text{S}_6$ (Johan *et al.*, 1994), monoclinic **museumite** $\text{AuPb}_5\text{SbTe}_2\text{S}_{12}$ (Bindi and Cipriani, 2004), rhombic **buckhornite** $\text{AuPb}_2\text{BiTe}_2\text{S}_3$ (Francis *et al.*, 1992; Johan *et al.*, 1994), monoclinic **criddleite** $\text{Au}_3\text{Ag}_2\text{TeSb}_{10}\text{S}_{10}$ (Harris *et al.*, 1988), monoclinic **jonnassonite** AuBi_5S_4 (Paar *et al.*, 2006) are typical formations of Au and Au-Ag volcanogenic hydrothermal deposits. Nagyágite – ‘grey foliated gold ore’ – is the most widespread among them.

11. PLUMBOTELLURIDES AND STIBIO-PLUMBOTELLURIDES OF THE Au-Cu-Fe SYSTEM

These hypergenic minerals are developed in the cementation zone of gold-telluride deposits. They are monoclinic (?) **bilibinskite** $\text{Au}_5\text{Cu}_3(\text{Te,Pb})_5$ and **bilibinskite-(Sb)** $\text{Au}_6\text{Cu}_2(\text{Te,Pb,Sb})_5$ (Spiridonov, 1991b), rhombic (?) **bogdanovite-(Cu)** – $\text{Au}_5\text{Cu}_3(\text{Te,Pb})_2$ and **bogdanovite-(Fe)** – $\text{Au}_5\text{CuFe}_2(\text{Te,Pb})_2$ (Spiridonov, 2008), monoclinic (?) **bezmertnovite** $\text{Au}_4\text{Cu}(\text{Te,Pb})$ (Spiridonov, 1991b). Bilibinskite, bogdanovite and bezsmertnovite contain ~

Figure 3: (See colour plate) Bogdanovite (pseudomorph after kostovite) in gold-quartz vein. 2 mm. Bogdanovite with strong coloured birefractive. Polished section in reflected light. Aginskoe, Kamchatka. Collection and photography – E.S.

Figure 3 : (Voir planche couleur) Bogdanovite (pseudomorphe de kostovite) dans le filon de quartz aurifère. Bogdanovite avec biréfractation fortement colorée. Section polie sous lumière réfléchie. Aginskoe, Kamchatka. Collection et photographie – E.S.

50, 65 and 75 wt% Au, respectively. Macroscopically, they have the appearance of bornite. In reflected light, they are very specific, being characterized by bright colour double-reflection (Fig. 3) and anisotropy. Bilibinskite, bogdanovite and bezsmertnovite replace kostovite, krennerite, silvanite, and nagyágite. In the oxidation zone, plumbotellurides of gold are substituted by finely scalloped gold and tellurides of Cu, Pb, and Fe.

12. CONCLUSION

Brief data on the 44 gold mineral species known today are provided above. Each of them has an individual chemical composition, crystal structure, X-ray pattern, unit cell parameters, physical properties (colour, hardness, spectra of reflection light, etc.). For many of these minerals, the most important feature is their fineness, i.e. Au content expressed in %.

A main new feature – new characteristic of gold minerals – could probably be related to the area sizes of X-radiation coherent dissipation, i.e. the crystallite size. For the majority of crystal matters, the crystallites' size is nano-dimensional, ranging from a few nm up to several hundreds of nm. The description of the crystallites size can be found in a paper by D. Yanakieva and co-authors in this issue of *ArcheoSciences*. The first interesting data on the nano-dimensions of crystallites is obtained. High-standard gold from large mesothermal deposits in Northern Kazakhstan, with an age of 445 ± 4 Ma, is studied. These deposits are of a different depth facies – hypabyssal Au-Sb Bestube, mesoabyssal Au Stepnyak, abyssal Au-telluride (Spiridonov, 1995). One of the studied specimens from Bestube is shown in Figure 1. The crystallite sizes of tens of studied Bestube gold specimens are 20.0 ± 0.2 nm; for Stepnyak gold, 21.6-21.8 nm; for Aksu gold, 26.0 ± 0.3 nm (investigator D. Yanakieva). Thus, for this group of deposits, the direct correlation between the size of crystallites and the depth of formed gold ores is established. The size of the crystallites of hypergenic gold from Zana-Tube is quite different: 31.3-31.8 nm.

Acknowledgements

This research was supported by grant no. 07-05-00057 of the Russian Foundation for Basic Research.

References

- AL-BIRUNI, A., 1963. *Materials for investigations of the precious stones*. Leningrad: Academy of Sciences USSR (in Russian).
- AMUZINSKY, V., ANISIMOVA, G. and ZDANOV, YU., 1992. *Native gold of the Yakutia: Verkhne-Indigirskii region*. Novosibirsk: Nauka (in Russian).
- BARTON, M., KIEFT, C., BURKE, E. and OEN, I., 1978. Uyténbogaardtite, a new silver-gold sulfide. *The Canadian Mineralogist* 16: 651-657.
- BERMAN, H. and HARCOURT, G., 1938. Natural amalgams. *American Mineralogist* 23: 761-764.
- BERMAN, YU., BOTOVA, M., BOCHEK, L. and PLESCHAKOV, A., 1978. Natural system of the gold – silver. *Geochemistry* 9: 1351-1359 (in Russian).
- BINDI, L. and CIPRIANI, C., 2004. Museumite, $\text{AuPb}_5\text{SbTe}_2\text{S}_{12}$, a new mineral from the gold-telluride deposit of Sacarimb, Metaliferi Mountains, western Romania. *European Journal of Mineralogy* 16: 835-838.
- BOCHEK, L., SANDOMIRSKAYA, S., CHUVIKINA, N. and KHOSTOV, V., 1984. New selenian sulfide of the silver, gold and copper – penzinite $\text{Au}(\text{Ag}, \text{Cu})_4(\text{S}, \text{Se})_4$. *Zapiski Vsesoyznogo Mineralogicheskogo. Obshchestva* 113: 356-360 (in Russian).
- BRAUNS, R., 1906. *Kingdom of minerals*. St. Petersburg: A.F. Devrien. (in Russian).
- CHEN, K., TINGGAO, Z. and PENG, Z., 1982. Tetraauricupride, CuAu , discovered in China. *Scientia. Geologica Sinica* 11(1): 111-116 (in Chinese with English abstract).
- CHEN L., , TANG, C., ZHANG, J. and LIU, Z., 1994. A new auriferous and stanniferous mineral, *Acta Petrologica Et Mineralogica* 13(3): 232-238 (in Chinese with English abstract).
- CHVILEVA, T., BEZSMERTNAYA, M. and SPIRIDONOV, E. (eds), 1988. *Reference book for determination of the ore minerals in reflected light*. Moscow, Nedra (in Russian).
- EDITORIAL COMMITTEE FOR “INTRODUCTION TO JAPANESE MINERALS”, ORGANIZING COMMITTEE IMA-IAGOD MEETINGS, '70, 1970. *Introduction to Japanese minerals*. Tokyo, Geological Survey of Japan.
- FRANCIS, C., CRIDDLE, A. and STANLEY, C., 1992. Buckhornite, $\text{AuPb}_2\text{BiTe}_2\text{S}_3$, a new mineral species from Boulder County, Colorado, and new data for aikinite, tetradymite and calaverite. *The Canadian Mineralogist* 30: 1039-1048.
- FRIMMEL, H. and GARTZ, V., 1997. Witwatersrand gold particle chemistry matches model of metamorphosed, hydrothermally altered placer deposits. *Mineralium Deposita* 32: 523-531.
- NEDRA 1984-1990. *Gold deposits of the Soviet Union*. Vol. 1-5. Moscow, Nedra Press (in Russian).
- GOLDSCHMIDT, V.M., 1918. *Atlas der Krystallformen*. Gold. Band IV. Heidelberg, Carl Winters Universitätsbuchhandlung.

- GRAHAM, A. and CAIMAN, S., 1952. Auostibite, AuSb_2 , a new mineral in the pyrite group. *American Mineralogist* 37: 461-469.
- HARRIS, D., ROBERTS, A. and LAFLAMME, J., 1988. Criddleite $\text{TiAg}_2\text{Au}_3\text{Sb}_{10}\text{S}_{10}$, a new gold-bearing mineral from Hemlo, Ontario, Canada. *Mineralogical Magazine* 52: 691-697.
- HYTÖNEN, K., 1999. *Suomen Mineraalit*. Erillisjulkaisien, Geologian Tutkimuskeskus.
- JOHAN, Z., DODONY, I., MORAVEK, P. and PAŠAVA, J., 1994. Le buckhornite, $\text{Pb}_2\text{AuBiTe}_2\text{S}_3$, du gisement d'or de Jilove, République Tchèque. *Comptes Rendus de l'Académie des Sciences Paris* 318: 1225-1231.
- JOHAN, Z., PICOT, P., PIERROT, P. and KVAČEK, M., 1971. La fischesserite, Ag_3AuSe_2 , premier sélénide d'or, isotype de la petzite. *Bulletin de la Société française de minéralogie et de cristallographie* 94: 381-384.
- KNIPE, S. and FLEET, M., 1997. Gold-copper alloy minerals from the Kerr-Edison Mine, Ontario. *The Canadian Mineralogist* 35: 573-586.
- KNIGHT, J. and LEITCH, C.H.B., 2001. Phase relations in the system Au–Cu–Ag at low temperatures, based on natural assemblages, *The Canadian Mineralogist* 39: 889-905.
- KNITTEL U., 1989. Composition and association of arsenian goldfieldite from the Marian Gold deposit, Northern Luzon, Philippines // *Mineral. Petrol.* 40: 145-154.
- KWITKO, R., CABRAL, A., LEHMANN, B., LAFLAMME, J., CABRI, L., CRIDDLE, A. and GALBIATTI, H., 2002. Hongshiite, PtCu , from itabirite-hosted Au–Pd–Pt mineralization, Itabira district, Minas Gerais, Brazil. *The Canadian Mineralogist* 40: 711-723.
- LEVIN, V., KOTEL'NIKOV, P. and KURNABAEV, E., 1986. Find of the natural intermetallide of gold and platinum intermetallide. *Izvestiya Akademii Nauk Kazakhskoy SSR Seriya Geologicheskaya*. 4: 76-80 (in Russian).
- LINDGREN, W., 1933. *Mineral deposits*, 4th ed. New York, London, McGraw-Hill Book Company.
- LOZETCHKIN, M., 1939. New data about chemical composition "cuprian" gold. *Doklady Academy of Sciences of the USSR* 24: 454-457 (in Russian).
- LYAKISCHEV, N.P. (ed.), 1996. 1997, 2001, *Diagrams of the state for double metallic systems*. Vol. 1: 1996. Vol. 2: 1997. Vol. 3: 2001. Moscow: Maschino stroenie (in Russian).
- MARKHAM, N., 1960. Synthetic and natural phases in the system Au–Ag–Te. *Economic Geology* 55: 1148-1178, 1460-1477.
- NAZMOVA, G. and SPIRIDONOV, E., 1979. Mercurian gold. *Doklady Academy of Sciences of the USSR* 246: 702-705 (in Russian).
- NEKRASOV, I., SAMUSIKOV, V., LESKOVA, N., 1988. First find of the sulfide AuAgS – analog at petrovskaite. *Doklady Academy of Sciences of the USSR* 303: 944-947 (in Russian).
- NEKRASOV, I.Y., LENNIKOV, A.M., OKTYABRSKY, R.A., ZALISHAK, B.L. and SAPIN, B.I. 1994. Petrology and platinum mineralization of the alkaline-ultramafic ring complexes, (Laverov, N.P. ed.). Moscow, Russia, Nauka, 381 p. (in Russian).
- NESTERENKO, G., KUZNEZOVA, A. and PAL'CHIK, N., 1984. Petrovskaite $\text{AuAg}(\text{S}, \text{Se})$ – new selenian sulfide of gold and silver. *Zapiski Vsesoyuznogo Mineralogicheskogo. Obshchestva* 113 (5): 602-607 (in Russian).
- OBERTHÜR, T. and SAAGER, R., 1986. Silver and mercury in gold particles from the Proterozoic Witwatersrand placer deposits of South Africa: metallogenic and geochemical implications. *Economic Geology* 81: 20-31.
- PAAR, W., PUTZ, H., TOPA, D., ROBERTS, A., STANLEY, C. and CULETTO, F., 2006. Jonassonite, $\text{Au}(\text{Bi}, \text{Pb})_5\text{S}_4$, a new mineral species from Nagybörzsöny, Hungary. *The Canadian Mineralogist* 44: 1127-1136.
- PEACOCK, M. and THOMPSON, R., 1946. Montbrayite, a new gold telluride. *American Mineralogist* 31: 515-526.
- PETROVSKAYA, N., 1973. *Native gold*. Moscow, Nauka (in Russian).
- RAMDOHR, P., 1967. A widespread mineral association, connected with serpentinization. *Neues Jahrbuch Mineralogie Monatshefte* 107S: 241-265.
- RAZIN, L. and SIDORENKO, G., 1989. Anyuuite AuPb_2 – new intermetallide of gold and lead. *Mineralogical Journal* 11(4): 88-92 (in Russian).
- SAMUSIKOV, V. and NEKRASOV, I., LESKOVA, N., 2002. Sulfoselenide $(\text{Ag}, \text{Au})_2(\text{S}, \text{Se})$ from Yakutskoe deposit. *Zap. VMO*. 131(6): 61-65 (in Russian).
- SHANGQUAN, W., YANG, Y. and SONG, Q., 1992. A new gold mineral – hunchunite (Au_2Pb) . *Acta Mineralogica Sinica* 12: 319-322.
- SHIKAZONO, N. and SHIMIZU, M., 1987. The Ag/Au ratio of native gold and electrum and the geochemical environment of gold deposits in Japan. *Mineralium Deposita* 22: 309-314.
- SHIKAZONO, N., SHIMIZU, M., 1988. Mercurian gold from the Tsugu gold-antimony vein deposit in Japan. *The Canadian Mineralogist* 26: 423-428.
- SIMON, G., ALDERTON, D. and BLESER, T., 1994. Arsenian nagyagite from Sacarimb, Romania: A possible new mineral species. *Mineralogical Magazine* 58: 473-478.
- SMOLIN, A., 1970. Nuggets of gold from the Urals. Moscow: Nedra (in Russian).
- SO, C.S., DUNCHENKO, Y., YUN, S., 1995. Te- and Se-bearing epithermal Au–Ag mineralization, Prasolovskoe, Kunashir Island, Kuril island arc. *Economic Geology* 90: 105-117.
- SPIRIDONOV, E., 1991a. Nagiagite $\text{AuPb}_5\text{Te}_{4-x}\text{Sb}_x\text{S}_6$. *The Fersman Mineralogical Museum, Russian Academy of Sciences* 37: 128-138 (in Russian).
- SPIRIDONOV, E., 1991b. About compositions and structures of the minerals bilibinskite – bogdanovite group. *Trans. Fersman Mineral. Museum* 37: 138-145 (in Russian).

- SPIRIDONOV, E., 1995.** Inversion plutonogenic gold-quartz formation in caledonides of the Central Kazakhstan. *Geology ore deposits* 37: 179-207 (in Russian).
- SPIRIDONOV, E., 2008.** Ferrian bogdanovite $\text{Au}_3\text{CuFe}_2(\text{Te,Pb})_2$ from the cementation zone of the Aginskoe gold-telluride deposit, Kamchatka. *The Fersman Mineralogical Museum, Russian Academy of Sciences* 43: 143-145 (in Russian).
- SPIRIDONOV, E. and CHVILEVA, T., 1985.** Mutmannite AuAgTe_2 – new data. *Doklady Academy of Sciences of the USSR* 280: 994-997 (in Russian).
- SPIRIDONOV, E. and PLETNEV, P., 2002.** Deposit of the cuprian gold Zolotaya Gora. Moscow: Scientific World (in Russian).
- SPIRIDONOV, E., KULAGOV, E. and KULIKOVA, I., 2003.** Platinian-palladian tetraauricuprid and associated minerals from Noril'sk-I ore deposit. *Geology ore deposits* 45: 267-277 (in Russian).
- SPIRIDONOV, E., FILIMONOV, S. and BZYZGALOV, I., 2009.** Solid solution fischesserite –naumannite $(\text{Ag,Au})_2\text{Se}$ from the volcanogenic gold deposit Ozerovskoe, Kamchatka. *Doklady Academy of Sciences of the USSR* 425: 391-394 (in Russian).
- STILLWELL, F., 1931.** The occurrence of telluride minerals of Kalgoorlie. *Proceedings of the Australian Institute for Mining and Metallurgy* 84: 115-190.
- TERZIEV, G., 1966.** Kostovite, a gold-copper tellurid from Bulgaria. *American Mineralogist* 51: 29-36.
- VERNADSKY, V.I., 1914.** Experience of the descriptive mineralogy. Petrograd, Imperial Academy of Sciences (in Russian).
- WU, S., 1993.** Hypothesis of amalgamation overgrowth of placer gold. *30th International Geological Congress, Beijing 1993. Quaternary Geology*, A. Zhisheng, Z. Weijian eds. Vol. 3, VSP. Utrecht, The Netherlands. 3235.
- YAKUBOVSKAYA, N., SPIRIDONOV, E., PONOMAREVA, I. and GAPEEV, A., 1989.** About “magnetic” native gold. *Doklady Academy of Sciences of the USSR* 309: 434-437 (in Russian).